

<b>QUALITY :</b>	<b>APOLLO/ REGENCY</b>
------------------	------------------------

<b>FABRIC DESCRIPTION</b>	<b>METHOD</b>	
COMPOSITION % POLYESTER		<b>65</b>
COMPOSITION % COTTON		<b>35</b>
USABLE WIDTH (cms)	BS EN 1773	<b>150</b>
NOMINAL LENGTH (mts)		<b>100</b>
WEAVE		<b>2x1</b>
WEIGHT g/sm	BS EN 12127	<b>190</b>

<b>PHYSICAL PROPERTIES</b>	<b>METHOD</b>	<b>WARP</b>	<b>WEFT</b>
TENSILE STRENGTH NEWTONS (MIN)	BS EN ISO 13934	<b>1000</b>	<b>500</b>
TEAR STRENGTH NEWTONS (MIN)	BS EN ISO 13937-3	<b>20</b>	<b>20</b>
% SHRINKAGE TO WASHING (MAX) 60C	BS EN ISO 26330	<b>3</b>	<b>3</b>

ABRASION RESISTANCE RUBS	BS EN ISO 12947	<b>25000</b>
PILLING RESISTANCE 10 HOURS	BS EN ISO 12945-1	<b>4</b>

<b>COLOUR FASTNESS</b>	<b>METHOD</b>	<b>CHANGE</b>	<b>STAIN(PE)</b>	<b>STAIN(CTN)</b>
WASHING	BS EN ISO 105 C06 C2S	<b>4</b>	<b>3</b>	<b>3-4</b>
ACID PERSPIRATION	BS EN ISO 105 E04	<b>4</b>	<b>3</b>	<b>3-4</b>
ALKALI PERSPIRATION	BS EN ISO 105 E04	<b>4</b>	<b>3</b>	<b>3-4</b>
RUB FASTNESS (WET)	BS EN ISO 105 X12			
RUB FASTNESS (WET)	BS EN ISO 105 X12			<b>2-3</b>
RUB FASTNESS (DRY)	BS EN ISO 105 X12			<b>3-4</b>
LIGHT FASTNESS	BS EN ISO 105 B02	<b>4</b>		

THE ABOVE FIGURES ARE GUIDELINES ONLY AND SLIGHT VARIATIONS WITHIN COMMERCIAL TOLERANCES MAY OCCUR FROM TIME TO TIME.

THE SHRINKAGE WASHES ARE FOR ONE WASH ONLY, FURTHER WASHES WILL RESULT IN PROGRESSIVE SHRINKAGE PARTICULARLY ON COTTONS, AND CARE SHOULD BE TAKEN IN SIZING GARMENTS.

PLEASE CONSULT YOUR SUPPLIER IF IN ANY DOUBT.

ISSUE: 07.07.15